

Product data sheet

Glass fabric 210 g/m²

Technical properties

Parameter	Value	Standard
Weave	Plain	DIN ISO 9354
Weight	206 g/m ² +/- 5%	DIN EN 12127
Yarn Warp Weft	EC9-68 +/- 5% EC9-68 +/- 5%	DIN EN 12654
Thread count Warp Weft	17.2 1/cm +/- 5% 12.0 1/cm +/- 5%	DIN EN 1049
Tensile strength Warp Weft	500 N/cm 350 N/cm	DIN EN 12654
Combustible mater content	2,00 - 4,00 %	DIN ISO 1887
Fabric thickness	0,18 mm	DIN ISO 4603/E
Temperature resistance Continual Temporary	250 C ⁰ 500 C ⁰	



Rockwool A/S
DK-2640 Hedehusene
Tel.: +45 46 56 16 16
Fax: +45 46 56 16 04
E-mail: export@rockwool.dk
Internet: www.rockwool-marine.com

Rockwool Marine & Offshore
Hong Kong Office
Suite 1303, Asia Orient Tower, Town Place
33 Lockhart Road, Wanchai, Hong Kong
Tel: +852 2866 6180
Fax: +852 2866 9555

*Rockwool A/S reserves the
right to make necessary
product changes at any time.
Technical specifications are
thus stated subject to change.*