

Product data sheet

S 337 Alu tape

Product description

Aluminium foil. 30 micron with interleaving.

Features and Benefits

- Very soft and very conformable
- Easy tear
- Same aluminium appearance as air duct



Application

Ensuring an airtight surface between two batts.
Low flame spread approval.

Technical properties

Parameter	Value	Standard
Thickness	0.06 mm ± 0.02	AFERA 4006
Adhesion to steel	4.0 N/cm ²	AFERA 4001
Tensile strength	12 N/cm ²	AFERA 4004
Elongation at break	5%	AFERA 4005
Approvals	IMO A.653 (16) UL 723 BS 476 Part 6 British building regulation SISIR ISO 9001	
Operating temperature	-20 °C to +110 °C	
Storage	The rolls of tape must be stored flat on their cut edges in the original packing until required for use, and must be protected from dust, heat, moisture, direct sunlight, corrosion and solvent fumes at a recommended temperature of 10°C to 25°C It is recommended that the tape be used within 12 months after receipt of the material.	



Rockwool A/S
DK-2640 Hedehusene
Tel.: +45 46 56 16 16
Fax: +45 46 56 16 04
E-mail: export@rockwool.dk
Internet: www.rockwool-marine.com

Rockwool Marine & Offshore
Hong Kong Office
Suite 1303, Asia Orient Tower, Town Place
33 Lockhart Road, Wanchai, Hong Kong
Tel: +852 2866 6180
Fax: +852 2866 9555



Rockwool A/S reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.